



PRODUCT NAME

LAZY JACK
BRAID

CORE : Polyester HT

COVER : Polyester HT

FIBER CHARACTERISTICS

The fiber's components of this product are : **POLYESTER HT**

- **Polyester** it's polymers produced by mixing ethylene glycol and terephthalic acid.



FIBER'S PROPERTY	UDM	POLYESTER HT	-	-	-
Tenacity	gr/den	9,3	-	-	-
Specific gravity	gr/cm ³	1,38	-	-	-
Elongation at break	%	14,6	-	-	-
Tensile modulus	gr/den	120	-	-	-
Melting point	°C	256	-	-	-

ANIMA : POLIESTERE HT




----- Tenacità ----- POLYESTER



COVER TECH MIX : ABSENT

CORE



POLYESTERE HT

COVER

ABSENT



BRAID CHARACTERISTICS

CORE			COVER (it's a media of the of all fiber's components)		
Tenacity	9,3	gr/den	Abrasion resistance	-	gr/den
Creep	10	%	Peack of temp.	-	°C
Module	120	gr/den	Grip	-	frict. coeff.
Weight	1,38	gr/cm ³	Weight	-	gr/cm ³

DISCOUNT SYSTEM

SHOP		WHOLESALE	
Standard lenght sc.	%	Standard lenght sc.	%
-	-	-	-
-	-	-	-

APPLICATIONS , TECHNICAL DATA , PRICE

- Lazy jack line

 grey			
---	--	--	--

Ø	weight	breacking load	standard lenght	custom lenght	Ø	white	-	-	-
mm	gr/mt	daN	mt	mt	mm	€/mt	-	-	-
4	11,0	500	200	-	4	0,600 €	-	-	-
5	17,0	800	200	-	5	0,800 €	-	-	-
6	26,5	1.000	200	-	6	1,000 €	-	-	-
8	41,0	1.700	200	-	8	1,600 €	-	-	-
10	60,0	2.500	200	-	10	2,300 €	-	-	-

* Linear breaking load in according to DIN EN ISO 2307